## **MIRAFI** RSi

**MIRAFI**° RSi Series is a revolutionary geotextile created from super high-tenacity polypropylene filaments formed into an innovative weave to provide superior reinforcement strength and soil interaction integrated with high water flow and soil retention capabilities. It is extremely robust and suitable for laying directly over soft subgrade with minimum manpower.

Properties		<b>Test Standard</b>	Unit	RS 380i	RS 580i
Mechanical					
Characteristic Tensile Strength at 2% Strain	CD	ASTM D4595	kN/m	20	26
Characteristic Tensile Strength at 2% Strain	MD	ASTM D4595	kN/m	8	9
CBR Puncture Strength		ASTM D6241	N	6600	9000
Grab Strength		ASTM D4632	N	1500	2100
Trapezoidal Tear Strength		ASTM D4533	N	600	700
G-Rating		Austroads	-	7000¹	10000¹
Hydraulic					
Flow Rate		ASTM D4491	I/m²/min	3050	3050
Permittivity		ASTM D4491	sec <sup>-1</sup>	0.9	1.0
Soil Retention					
Apparent Opening Size, O <sub>95</sub>		ASTM D4751	mm	0.43	0.43
Effective Opening Size, O <sub>90</sub>		ISO 12956	mm	0.35	0.30
Soil Interaction					
Interaction Coefficient (Direct Shear)		ASTM D5321	-	0.801	$0.80^{1}$
Interaction Coefficient (Pull-out)		ASTM D6706	-	$0.89^{1}$	$0.90^{1}$
Resistance to Installation Damage		ASTM D5818	% strength retained	90 <sup>1</sup>	901
UV Resistance (at 500 hours)		ASTM D4355	% strength retained	90	90
Physical Properties					
Roll Dimension (width x length)			m	4.6 x 100	4.6 x 100
Roll Area			m	460	460

## NOTES:

## TenCate Geosynthetics Asia Sdn. Bhd. – A Solmax company

199301009495 (264232-U) 14, Jalan Sementa 27/91, Seksyen 27, 40400 Shah Alam, Selangor Darul Ehsan, Malaysia Tel: +60 3 5192 8568 | Fax: +60 3 5192 8575







infoasia@solmax.com

Solmax is not a design or engineering professional and has not performed any such design services to determine if Solmax's goods comply with any project plans or specifications, or with the application or use of Solmax's goods to any particular system, project, purpose, installation, or specification.

MIRAFI® is a registered trademarks of Solmax in many countries of the world.



<sup>(1)</sup> G-Rating, interaction coefficient (for sand or gravel) and resistance to installation damage (for sandy gravel) values are based on tests conducted by external test laboratories.